

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08L 25/06, 69/00, 33/12, 55/02, 25/12, 67/02, 67/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/50347</b> <b>(43) International Publication Date:</b> 7 October 1999 (07.10.99)
<b>(21) International Application Number:</b> PCT/GB99/00946 <b>(22) International Filing Date:</b> 25 March 1999 (25.03.99) <b>(30) Priority Data:</b> 9806631.9                      28 March 1998 (28.03.98)                      GB <b>(71) Applicant (for all designated States except US):</b> SAFEGLASS (EUROPE) LIMITED [GB/GB]; James Watt Building, Scottish Enterprise Technology Park, East Kilbride G75 0QD (GB). <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> McNEILL, Ralph [GB/GB]; James Watt Building, Scottish Enterprise Technology Park, East Kilbride G75 0QD (GB). <b>(74) Agent:</b> KENNEDY & CO.; Station House, 34 St. Enoch Square, Glasgow G1 4DF (GB).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> SAFETY GLASS		
<b>(57) Abstract</b>  Material for use as safety glass comprises a mixture of polymeric material and a thermoplastic polystyrene resin having a molecular weight of between 500 and 5000. The polymeric material is selected from high molecular weight impact or crystal polystyrene, polycarbonate, acrylic polymers, ABS, SAN and polyester. The material may further comprise ingredients selected from the list of UV inhibitors, antioxidants, flow modifiers, fire retarding agents, colour pigments and brighteners. The material is typically used in emergency equipment, glassware and windows.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## 1 SAFETY GLASS

2

3 The present invention relates to a type of safety glass,  
4 particularly safety glass that can be used in storage  
5 containers for emergency equipment.

6

7 At present there are several emergency devices where  
8 glass is used. The glass is used for its transparency  
9 and breakable properties, so that the person using the  
10 emergency device, such as a fire-axe, can not only  
11 observe the presence of the safety article in its  
12 retaining box but can also easily break the glass to  
13 access the device when required. Glass finds similar  
14 applications in emergency door releases, fire alarm  
15 activators and many other emergency devices.

16

17 The problem with the use of glass in such applications is  
18 that the glass must be broken to access the device to be  
19 used. Often there is a subsidiary device that can be  
20 used to break the glass. However, this may be missing or  
21 not be supplied as part of the device. In either case  
22 the breakage of the glass will cause the previously  
23 harmless sheet of glass to be broken into sharp glass  
24 fragments and also glass splinters.

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34

Needless to say the presence of sharp glass poses an unnecessary hazard to the user, particularly if the sharp glass injures the user in an attempt to access a safety device.

The use of glass may often present other problems to the potential user of a safety device, for example that person may assume that the glass used is safety glass and be surprised at any damage that they inflict upon themselves and any others. The potential user may also question as to whether they can access the device without causing any damage to themselves, any such time wasted in the case of an emergency could be crucial and should be avoided.

It is also possible that malicious or accidental damage may occur and the layer of glass in the retaining device may be broken in a non-emergency situation. In any case there may be sharp fragments of glass left behind, which can be a danger to passers by.

Also some organisations now insist upon either a strict control of glass usage within their buildings or the complete prohibition of the use of glass. Some areas of hospitals and food preparation are now insistent on being glass free zones.

There has already been considerable research carried out on products that can be used to replace glass. One such product is perspex, which like glass is transparent and being a polymeric material should not produce the same shards as are produced by breaking glass.

1 However, the use of perspex and its related plastics is  
2 not without its problems. Perspex can be harder to break  
3 than glass as it is not as fragile and can still produce  
4 sharp fragments that can injure the user in the same way  
5 as glass can.

6

7 It is an object of the present invention to provide an  
8 improved material for use as safety glass.

9

10 According to the present invention there is provided a  
11 material having a tensile stress limit of between 11 and  
12  $60 \text{ Nmm}^{-2}$ , that is or can be made transparent and can be  
13 made into sheets/structures just like ordinary glass, but  
14 that shatters when broken into fragments that are not  
15 capable of damaging human skin or tissue and which is  
16 comprised of a mixture of polymeric material and/or a  
17 thermoplastic polystyrene resin and/or a thermoplastic  
18 vinylaromatic resin.

19

20 Preferably the polymeric material is chosen from the  
21 group consisting of crystal or impact polystyrene,  
22 polycarbonate, acrylic, ABS (acrylonitrile butadiene  
23 styrene), SAN (styrene and acrylic blend) and polyester.

24

25 Preferably the thermoplastic polystyrene resin is chosen  
26 from the group consisting of co-polymers of styrene and  
27 alpha methyl styrene, hydrogenated aliphatic polymer and  
28 styrene monomer.

29

30 Preferably also the thermoplastic polystyrene resin has a  
31 molecular mass of between 500 and 5000.

32

33 Preferably also the safety glass of the present invention  
34 includes other ingredients selected from the list of UV

1 inhibitors, antioxidants, flow modifiers, fire retarding  
2 agents, colour pigments and brighteners.

3

4 Preferably these ingredients are present in the safety  
5 glass of the present invention at between 0.001% and  
6 0.01%.

7

8 Preferably the safety glass of the present invention can  
9 be etched upon.

10

11 In a preferred embodiment of the invention the safety  
12 glass of the present invention is composed of crystal or  
13 impact polystyrene (0-85%) and thermoplastic polystyrene  
14 resin (0-15%) together with 0.001% to 0.01% UV  
15 inhibitors, antioxidants, flow modifiers, fire retarding  
16 agents, colour pigments and brighteners, which gives a  
17 safety glass material which has a stress limit of between  
18 11 and 60 Nmm<sup>-2</sup>.

19

20 The preferred embodiment of the invention can be used in  
21 such applications as emergency equipment enclosures (key  
22 boxes, first aid boxes, fire extinguisher enclosures,  
23 window hammer enclosures, access panels, door egresses  
24 housing manually operated door handles), break glass fire  
25 alarms and emergency kick out panels.

26

27 The preferred embodiment of the invention can also be  
28 used in other applications such as drinking glasses,  
29 bottles and non-emergency windows, preventing injuries  
30 from conventional glass in these applications.

31

32 The mechanism which makes safeglass break, and break into  
33 safe parts is the low molecular weight of the material.

34 Low molecular weight in polymers is a function of the

1 length of the chains. In this case the polystyrene resin  
2 has a very low molecular weight, too low in fact to be of  
3 any use, and also difficult to mould. By mixing low  
4 molecular weight polystyrene resin in the molecular mass  
5 range 500-5000 to crystal or high impact polystyrene it  
6 has the effect of lowering the stress limit of the  
7 latter. The resulting material is suitable for the  
8 present invention and processing it is greatly improved.  
9 The same theory applies to any other clear plastic, such  
10 as PMMA (acrylic) for example. By mixing low molecular  
11 weight acrylic to high molecular weight acrylic a new  
12 material could be produced. In this case we would be  
13 looking to produce a material with a molecular weight of  
14 approximately 3000 for it to be of any use.

15

16 Two important applications:

17

18 1. GLASSWARE AND BOTTLES: 12000 drink related incidents  
19 happen every week. The Home Office are to order  
20 magistrates to tighten conditions of pub and club  
21 licences to use toughened glasses to serve beer. This  
22 will reduce the injuries caused when glasses are used  
23 as weapons, currently running at 5500 per year.  
24 Safeglass glasses and bottles could play an important  
25 safety and security role in clubs or live events, they  
26 would also be cheaper than glass.

27

28 2. WINDOWS: Windows set in interior doors have to be made  
29 of toughened glass if they are fitted below a certain  
30 height, this is to save small children or fall victims  
31 from injury. However it is very expensive and still  
32 produces tiny cubes of sharp glass. Safeglass is safer  
33 and less expensive.

34

1 The safety glass of the present invention will now be  
2 described with reference to the following examples.

3

4 **Example 1**

5

6 The safety glass of the preferred embodiment of the  
7 invention is composed of crystal or impact polystyrene  
8 and an intermediate weight polystyrene resin (of  
9 molecular mass 500 to 5000). This material can be  
10 manufactured with a stress limit of between 11 to 60 Nmm<sup>-2</sup>.  
11

12

13 The following table shows the variation of the stress  
14 limit value of the preferred embodiment of the safety  
15 glass of the present invention.

16

17 **Table 1**

18

SAFEGlass NO.	% CRYSTAL/IMPACT POLYSTYRENE	% POLYSTYRENE RESIN	STRESS LIMIT
1	0	100	11
2	5	95	12
3	10	90	13
4	15	85	14
5	20	80	15
6	25	75	16
7	30	70	16.4
8	35	65	17
9	40	60	18.4
10	45	55	19
11	50	50	19.5
12	55	45	21
13	60	40	27
14	75	25	39
15	80	20	50
16	85	15	60

19


20



1 This information is also represented graphically in  
2 Figure 1.

3

4 **Figure 1**



5

6

7 To determine which safety glass composition is to be used  
8 in a particular application a stress calculation must be  
9 carried out using the following formula.

1   **Formula 1**

2

$$3 \qquad S = \frac{3 F L}{2 b h^2}$$

5

6   where        S is the stress limit in N/mm<sup>2</sup>  
7                F is the force in Newtons  
8                L is the length of the panel in metres  
9                b is the width of the panel in metres  
10               h is the depth of the panel in metres

11

12   **Example 2**

13

14   As Example 1 with the inclusion of the thermoplastic  
15   resin obtained by polymerisation of various vinylaromatic  
16   monomers.

17

18   **Example 3**

19

20   As Example 2 except that the crystal/impact polystyrene  
21   is replaced by polycarbonate.

22

23   **Example 4**

24

25   As Example 2 except that the crystal/impact polystyrene  
26   is replaced by acrylonitrile.

27

28   **Example 5**

29

30   As Example 2 except that the crystal/impact polystyrene  
31   is replaced by ABS (acrylonitrile butadiene styrene).

32

1   **Example 6**

2

3   As Example 2 except that the crystal/impact polystyrene  
4   is replaced by SAN (styrene and acrylic blend).

5

6   **Example 7**

7

8   As Example 2 except that the crystal/impact polystyrene  
9   is replaced by polyester.

10

11   Further modifications and improvements may be added  
12   without departing from the scope of the invention herein  
13   intended.

Claims:

1. A material having a tensile stress limit of between 11 and 60 Nmm<sup>-2</sup>, that is or can be made transparent and can be made into sheets/structures just like ordinary glass, but that shatters when broken into fragments that are not capable of damaging human skin or tissue and which is comprised of a mixture of polymeric material and/or a thermoplastic polystyrene resin and/or a thermoplastic vinylaromatic resin.
2. A material as claimed in Claim 1 wherein the polymeric material is chosen from the group consisting of crystal or impact polystyrene, polycarbonate, acrylic, ABS (acrylonitrile butadiene styrene), SAN (styrene and acrylic blend) and polyester.
3. A material as claimed in Claim 1 or 2 wherein the thermoplastic polystyrene resin is chosen from the group consisting of co-polymers of styrene and alpha methyl styrene, hydrogenated aliphatic polymer and styrene monomer.
4. A material as claimed in Claim 3 the thermoplastic polystyrene resin has a molecular mass of between 500 and 5000.
5. A material as claimed in any one of the preceding Claims wherein said material further includes ingredients selected from the list of UV inhibitors, antioxidants, flow modifiers, fire retarding agents, colour pigments and brighteners.

1 6. A material as claimed in Claim 5 wherein the  
2 ingredients are present at between 0.001% and 0.01%.

3

4 7. A material as claimed in any one of the preceding  
5 Claims wherein said material may be etched upon.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/GB 99/00946

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L25/06 C08L69/00 C08L33/12 C08L55/02 C08L25/12  
C08L67/02 C08L67/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	ABETZ V ET AL: "THE GLASS TRANSITION OF MIXTURES OF POLYSTYRENE WITH ALKYL-TERMINATED OLIGOSTYRENE - EXPERIMENTAL EVIDENCE FOR MICROPHASE SEPARATION IN A POLYMER BLENDS" MACROMOLECULAR CHEMISTRY AND PHYSICS, vol. 196, no. 11, 1 November 1995 (1995-11-01), pages 3845-3857, XP000583913 ISSN: 1022-1352 page 3847, Tab. 1, "Blend preparation"	1-4, 7
X	WO 97 15868 A (MINNESOTA MINING & MFG) 1 May 1997 (1997-05-01) page 7, line 12-24 page 18, line 10-24 --- -/--	1, 2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance  
"E" earlier document but published on or after the international filing date  
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  
"O" document referring to an oral disclosure, use, exhibition or other means  
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone  
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.  
"&" document member of the same patent family

Date of the actual completion of the international search

- 10 August 1999

Date of mailing of the international search report

19/08/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Rodriguez, L

# INTERNATIONAL SEARCH REPORT

Int'l Application No  
PCT/GB 99/00946

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 29383 A (DOW CHEMICAL CO) 22 December 1994 (1994-12-22) claims 1,4; tables 3,5 ---	1-7
A	DE 22 39 356 A (BASF AG) 21 February 1974 (1974-02-21) page 2, line 3-33 -----	1-7

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/00946

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9715868 A	01-05-1997	AU 706152 B AU 5577596 A CN 1200182 A EP 0857321 A	10-06-1999 15-05-1997 25-11-1998 12-08-1998
WO 9429383 A	22-12-1994	US 5422378 A AT 177132 T CA 2161887 A DE 69416833 D DE 69416833 T EP 0701589 A ES 2127929 T FI 955792 A HU 75497 A JP 8511055 T NO 954900 A	06-06-1995 15-03-1999 22-12-1994 08-04-1999 01-07-1999 20-03-1996 01-05-1999 01-12-1995 28-05-1997 19-11-1996 01-02-1996
DE 2239356 A	21-02-1974	BE 803358 A FR 2195642 A JP 49075660 A NL 7310843 A	08-02-1974 08-03-1974 22-07-1974 12-02-1974